Docusign Envelope ID: 4F33A0DB-2A37-85C5-8251-8A39808FB123

Fiesta Compostable/Recyclable, Fourth Way, Avonmouth, Bristol, BS11 8TB
Tel: 0117 316 5000 | Email: enquiries@fiestafoodtogo.com

Food Contact Declaration of Compliance

Declaration Identification No:	FCMD-Fiesta-001

Declaration of Compliance *(tick all that apply)*

☒	On materials and articles in contact with food Regulation (EC) No 1935/2004
☒	Good Manufacturing Practices (GMP, Commission Regulation (EC) No 2023/2006)
☐	BPA and other hazardous bisphenols in materials and articles that come into contact with food Commission Regulation (EU) 2024/3190
☒	Plastic monomers and additives in Regulation 10/2011
☐	For active/intelligent materials in Regulation 450/2009
☐	For recycled plastic processes in Regulation 282/2008
☐	Fo regenerated cellulose film in The Materials and Articles in Contact with Food (England) Regulations 2012

Identification of Food Contact Material

Product Code	Description	Material Type *(e.g. PP / PET / PE / PS – as applicable)*	Intended Use
GF018	Fiesta Recyclable Espresso Cups Single Wall Black - 114ml (4oz)(Box 1000)	PE+ Paper	Tea/Coffee
GF019	Fiesta Recyclable Espresso Cups Single Wall Black - 114ml (4oz)(Sleeve 50)	PE+ Paper	Tea/Coffee
GF030	Fiesta Recyclable Hot Cups Single Wall Kraft - 228ml (8oz) (Box 1000)	PE+ Paper	Tea/Coffee
GF031	Fiesta Recyclable Hot Cups Single Wall Kraft-228ml (8oz)(Sleeve 50)	PE+ Paper	Tea/Coffee
GF032	Fiesta Recyclable Hot Cups Single Wall Kraft - 341ml (12oz) (Box 1000)	PE+ Paper	Tea/Coffee
GF033	Fiesta Recyclable Hot Cups Single Wall Kraft-341ml (12oz) (Sleeve 50)	PE+ Paper	Tea/Coffee
GF034	Fiesta Recyclable Hot Cups Single Wall Kraft -455ml (16oz) (Box 1000)	PE+ Paper	Tea/Coffee
GF035	Fiesta Recyclable Hot Cups Single Wall Kraft - 455ml (16oz) (Sleeve 50)	PE+ Paper	Tea/Coffee
GF040	Fiesta Recyclable Hot Cups Single Wall Black - 228ml (8oz)(Box 1000)	PE+ Paper	Tea/Coffee
GF041	Fiesta Recyclable Hot Cups Single Wall Black -228ml (8oz)(Sleeve 50)	PE+ Paper	Tea/Coffee
GF042	Fiesta Recyclable Hot Cups Single Wall Black - 341ml (12oz)(Sleeve 1000)	PE+ Paper	Tea/Coffee
GF043	Fiesta Recyclable Hot Cups Single Wall Black - 341ml (12oz) (Sleeve 50)	PE+ Paper	Tea/Coffee

Docusign Envelope ID: 4F33A0DB-2A37-85C5-8251-8A39808FB123

Fiesta Compostable/Recyclable, Fourth Way, Avonmouth, Bristol, BS11 8TB
Tel: 0117 316 5000 | Email: enquiries@fiestafoodtogo.com

GF044	Fiesta Recyclable Hot Cups Single Wall Black - 455ml (16oz) (Box 1000)	PE+ Paper	Tea/Coffee
GP400	Fiesta Recyclable Hot Cups Single Wall Aqua - 228ml (8oz) (Sleeve 50)	PE+ Paper	Tea/Coffee
GP401	Fiesta Recyclable Hot Cups Single Wall Aqua - 341ml (12oz) (Sleeve 50)	PE+ Paper	Tea/Coffee
GP403	Fiesta Recyclable Hot Cups Single Wall Aqua -228ml (8oz) (Box 1000)	PE+ Paper	Tea/Coffee
GP404	Fiesta Recyclable Hot Cups Single Wall Aqua - 341ml (12oz)(Box 1000)	PE+ Paper	Tea/Coffee
GP407	Fiesta Recyclable Hot Cups Single Wall Red - 341ml (12oz) (Sleeve 50)	PE+ Paper	Tea/Coffee
GP409	Fiesta Recyclable Hot Cups Single Wall Red - 228ml (8oz) (Box 1000)	PE+ Paper	Tea/Coffee
GP410	Fiesta Recyclable Hot Cups Single Wall Red - 341ml (12oz) (Box 1000)	PE+ Paper	Tea/Coffee
GP415	Fiesta Recyclable Hot Cups Single Wall Charcoal - 228ml (8oz) (Box 1000)	PE+ Paper	Tea/Coffee
GP416	Fiesta Recyclable Hot Cups Single Wall Charcoal - 341ml (12oz) (Box 1000)	PE+ Paper	Tea/Coffee
GP446	Fiesta Recyclable Espresso Cups Single Wall Kraft - 114ml (4oz)(Sleeve 50)	PE+ Paper	Tea/Coffee
GP447	Fiesta Recyclable Espresso Cups Single Wall Kraft - 114ml (4oz)(Box 1000)	PE+ Paper	Tea/Coffee
HC265	Fiesta Recyclable Portion Pot 50ml (pack 1000)	PE+ Paper	Tea/Coffee
HC266	Fiesta Recyclable Portion Pot 80ml (pack 1000)	PE+ Paper	Tea/Coffee
HC267	Fiesta Recyclable Portion Pot 100ml (pack 1000)	PE+ Paper	Tea/Coffee
HT464	Fiesta Recyclable Hot Cup Single Wall Kraft-6oz (pack 1000)	PE+ Paper	Tea/Coffee
HT468	Fiesta Recyclable Hot Cup Single Wall Black-6oz (pack 1000)	PE+ Paper	Tea/Coffee
HW631	Fiesta Recyclable Ice Cream Pot 3oz (pack 1000)	PE+ Paper	Tea/Coffee
HW632	Fiesta Recyclable Ice Cream Pot 8oz (pack 1000)	PE+ Paper	Tea/Coffee
HW633	Fiesta Recyclable Ice Cream Pot 12oz (pack 1000)	PE+ Paper	Tea/Coffee
HX280	Fiesta Recyclable Hot Cup Double Wall Festive 8oz (Box 500)	PE+ Paper	Tea/Coffee

Docusign Envelope ID: 4F33A0DB-2A37-85C5-8251-8A39808FB123

Fiesta Compostable/Recyclable, Fourth Way, Avonmouth, Bristol, BS11 8TB
Tel: 0117 316 5000 | Email: enquiries@fiestafoodtogo.com

HX282	Fiesta Recyclable Hot Cup Double Wall Festive 12oz (Box 500)	PE+ Paper	Tea/Coffee

Composition and BPA / Bisphenol Compliance

In accordance with applicable EU bisphenol requirements:

(1) Bisphenols or bisphenol derivatives intentionally used: None ☐ / Declared below ☐

☒	None
☐	Yes, declared in (2) below

(2) Where Bisphenols or bisphenol derivatives are intentionally used:
(If applicable complete table below):

Substance name	CAS number

The plastic food contact article does not contain intentionally added bisphenol A (BPA) or other restricted bisphenols unless explicitly declared and legally permitted.

Where applicable, compliance with specific migration limits (SMLs) for regulated substances has been verified.

I, the undersigned, declare that the equipment specified above conforms to the Regulations as stipulated within this Declaration.

Signed by:
Ashley Hooper
AB6DB7656FFB441...
Nisbets Limited
Avonmouth, United Kingdom – [22.04.2026]
Ashley Hooper
Group Head of Product Quality & Compliance

Migration Testing Compliance

Migration testing has been performed or substantiated to demonstrate compliance with EU requirements:

Overall Migration:
Verified in accordance with Regulation (EU) No 10/2011, using appropriate food simulants and time/temperature conditions representative of intended use.

Specific Migration:
Specific migration limits (SMLs) for regulated substances listed in Annex I of Regulation (EU) No 10/2011 have been assessed and confirmed as compliant, where applicable.

Testing Approach:

☒	Laboratory testing by an accredited laboratory
☐	Compliance substantiated using supplier declarations and worst-case calculation
☐	Combination of testing and risk-based assessment

Docusign Envelope ID: 4F33A0DB-2A37-85C5-8251-8A39808FB123

Fiesta Compostable/Recyclable, Fourth Way, Avonmouth, Bristol, BS11 8TB
Tel: 0117 316 5000 | Email: enquiries@fiestafoodtogo.com

Test Conditions Covered *(insert screenshot of test report to satisfy the following section)*:
Simulants, contact time, and temperature conditions reflect worst-case foreseeable use of the product.

Test Report:

Test Part Description :

Specimen No.	SGS Sample ID	Description	Material (claimed by the client)
SN1	TAO24-005027.001	transparent film	PE
SN2	TAO24-005027.002	white paper	PAPER
SN3	TAO24-005027.003	color paper cup	PAPER

Remarks :

(1) mg/dm² = milligram per square decimeter
(2) mg/kg = milligram per kilogram
(3) °C= degree Celsius
(4) < = less than
(5) MDL = Method Detection Limit
(6) ND = Not Detected (< MDL)

Paper and board used in food contact materials and articles, EDQM-Colour Fastness

Test Method : With reference to EN 646: 2018.

Simulant Used	Time	Temperature	Max. Permissible Limit	Result of 002	Conclusion
3% Acetic acid (W/V)	10 min	23±2°C	★	Grade 5	PASS

Simulant Used	Time	Temperature	Max. Permissible Limit	Result of 003	Conclusion
3% Acetic acid (W/V)	10 min	23±2°C	★	Grade 5	PASS

Notes :

(1) ★= Grade 5
(2) Grey Scale Rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good.
(3) These tests was subcontracted to SGS Shanghai chemical lab.

(EU) No 10/2011 and its amendment (EU) 2020/1245 Regulation-Overall migration

Test Method : With reference to Commission Regulation (EU) No 10/2011 of 14 January 2011 Annex III and Annex V for selection of condition and EN 1186-1:2002 for selection of test methods; EN 1186-3:2022 Test methods for overall migration in evaporable simulants

Docusign Envelope ID: 4F33A0DB-2A37-85C5-8251-8A39808FB123

Fiesta Compostable/Recyclable, Fourth Way, Avonmouth, Bristol, BS11 8TB
Tel: 0117 316 5000 | Email: enquiries@fiestafoodtogo.com

Simulant Used	Time	Temperature	Max. Permissible Limit	Result of 001 Overall migration	Conclusion
3% Acetic acid (W/V) (First migration)	2.0hr(s)	70°C	10mg/dm²	<3.0mg/dm²	PASS
Area/Volume			-	7.6dm²/kg	

Notes :

(1) Analytical tolerance of evaporable simulants is 2 mg/dm² or 12 mg/kg. Analytical tolerance of olive oil simulant is 3 mg/dm² or 20 mg/kg.
(2)Test condition & simulant were specified by client.

Regulation (EC) No 1935/2004 of the European Parliament and of the Council of 27 October 2004 - Sensorial examination odour and taste test

Test Method : With reference to DIN 10955: 2023.
No. of panelist: 6

Test Item(s)	Limit	*002*
Test media	-	Distilled water
Test time (hr)	-	2
Temperature (°C)	-	40
Area/volume(dm²/kg)	-	10.0
Sensorial examination odour (Point scale)	2.5	0.0
Sensorial examination taste (Point scale)	2.5	0.0
Conclusion		PASS

Notes :

Intensity scale (rounded at 0.5):

0 – no perceptible difference
1 – just perceptible difference
2 – slight difference
3 – marked difference
4 – strong difference

Paper and board used in food contact materials and articles, EDQM-Transfer of antimicrobial agents

Test Method : With reference to EN 1104: 2018

Docusign Envelope ID: 4F33A0DB-2A37-85C5-8251-8A39808FB123

Fiesta Compostable/Recyclable, Fourth Way, Avonmouth, Bristol, BS11 8TB
Tel: 0117 316 5000 | Email: enquiries@fiestafoodtogo.com

Simulant Used	Time	Temperature	Max. Permissible Limit	Result of 001 Overall migration	Conclusion
3% Acetic acid (W/V) (First migration)	2.0hr(s)	70°C	10mg/dm²	<3.0mg/dm²	PASS
Area/Volume			-	7.6dm²/kg	

Notes :

(1) Analytical tolerance of evaporable simulants is 2 mg/dm² or 12 mg/kg. Analytical tolerance of olive oil simulant is 3 mg/dm² or 20 mg/kg.
(2)Test condition & simulant were specified by client.

Regulation (EC) No 1935/2004 of the European Parliament and of the Council of 27 October 2004 - Sensorial examination odour and taste test

Test Method : With reference to DIN 10955: 2023.
No. of panelist: 6

Test Item(s)	Limit	*002*
Test media	-	Distilled water
Test time (hr)	-	2
Temperature (°C)	-	40
Area/volume(dm²/kg)	-	10.0
Sensorial examination odour (Point scale)	2.5	0.0
Sensorial examination taste (Point scale)	2.5	0.0
Conclusion		PASS

Notes :

Intensity scale (rounded at 0.5):

0 – no perceptible difference
1 – just perceptible difference
2 – slight difference
3 – marked difference
4 – strong difference

Paper and board used in food contact materials and articles, EDQM-Transfer of antimicrobial agents

Test Method : With reference to EN 1104: 2018

Docusign Envelope ID: 4F33A0DB-2A37-85C5-8251-8A39808FB123

Fiesta Compostable/Recyclable, Fourth Way, Avonmouth, Bristol, BS11 8TB
Tel: 0117 316 5000 | Email: enquiries@fiestafoodtogo.com

Test Item(s)	Limit	002
Bacillus subtilis ATCC No. 6633	★	Absent
Aspergillus niger ATCC No.6275	★	Absent
Conclusion		PASS

Notes :

(1) ★ = Absence of zone inhibition
(2) Absent denotes absence of Antimicrobic constituents which inhibits the growth of tested bacteria and fungus
(3) The test was subcontracted to SGS Shanghai chemical lab.

(EU) No 10/2011 and its amendment (EU) 2020/1245 Regulation-Specific migration of primary aromatic amine

Test Method : With reference to EN 13130-1: 2004, analysis was performed by LC-MS-MS.

Sample 001

Simulant Used : 3% Acetic acid (W/V)
Test Condition : 40 ℃ 2.0 hr(s)

Test Item(s)	Max. Permissible Limit	Unit	MDL	Test result
Migration times	-	-	-	First
Area/volume	-	dm^2/kg	-	6.0
2,4,5-Trimethylaniline(2,4,5-TMA)	0.002	mg/kg	0.002	ND
2,4-Toluenediamine(2,4-TDA)	0.002	mg/kg	0.002	ND
2-Methoxy-5-Methylaniline(2-M-5-MA)	0.002	mg/kg	0.002	ND
3,3'-Dimethylbenzidine(3,3'-DMB)	0.002	mg/kg	0.002	ND
4,4'-Diaminodiphenylether(4,4'-DPE)	0.002	mg/kg	0.002	ND
4,4'-Methylenedianiline(4,4'-MDA)	0.002	mg/kg	0.002	ND
4,4'-Methylenedi-o-toluidine(4,4'-MDoT)	0.002	mg/kg	0.002	ND
4-Aminobiphenyl(4-ABP)	0.002	mg/kg	0.002	ND
4-Chloro-Aniline(4-CA)	0.002	mg/kg	0.002	ND
4-Chloro-o-Toluidine(4-CoT)	0.002	mg/kg	0.002	ND
4-Methoxy-mphenylenediamine(4-M-mPDA)	0.002	mg/kg	0.002	ND
Benzidine(BNZ)	0.002	mg/kg	0.002	ND
o-Anisidine(o-ASD)	0.002	mg/kg	0.002	ND
o-Toluidine(o-T)	0.002	mg/kg	0.002	ND
1,3-phenylenediamine	0.002	mg/kg	0.002	ND
2-naphthylamine	0.002	mg/kg	0.002	ND
o-aminoazotoluene	0.002	mg/kg	0.002	ND

Docusign Envelope ID: 4F33A0DB-2A37-85C5-8251-8A39808FB123

Fiesta Compostable/Recyclable, Fourth Way, Avonmouth, Bristol, BS11 8TB
Tel: 0117 316 5000 | Email: enquiries@fiestafoodtogo.com

2-Amino-4-nitrotoluene	0.002	mg/kg	0.002	ND
3,3'-dichlorobenzidine	0.002	mg/kg	0.002	ND
3,3'-dimethoxybenzidine	0.002	mg/kg	0.002	ND
4,4'-methylene-bis-(2-chloro-aniline)	0.002	mg/kg	0.002	ND
4,4'-thiodianiline	0.002	mg/kg	0.002	ND
4-amino azobenzene	0.002	mg/kg	0.002	ND
Primary aromatic amine (other)	0.01	mg/kg	-	ND
1,3-Diiminoisoindoline	-	mg/kg	0.01	ND
3-Anisidine	-	mg/kg	0.002	ND
2-Amino-1-naphthalinesulfonic acid	-	mg/kg	0.005	ND
2-Ethoxyaniline	-	mg/kg	0.005	ND
5-Chloro-2-methoxylaniline	-	mg/kg	0.005	ND
2-Chloraniline	-	mg/kg	0.01	ND
4-Toluidine	-	mg/kg	0.002	ND
1,4-Phenylenediamine	-	mg/kg	0.002	ND
3-Chloroaniline	-	mg/kg	0.01	ND
3-Toluidine	-	mg/kg	0.002	ND
3-Amino-4-methoxybenzanilide	-	mg/kg	0.002	ND
2-Chloro-4-nitroaniline	-	mg/kg	0.005	ND
4-Chlor-3-methoxyaniline	-	mg/kg	0.005	ND
4-Ethoxyaniline	-	mg/kg	0.002	ND
3-Amino-4-methylbenzamide	-	mg/kg	0.002	ND
1,5-Diaminonaphthalene	-	mg/kg	0.002	ND
4-Aminobenzamide	-	mg/kg	0.005	ND
Aniline	-	mg/kg	0.002	ND
4-Chlor-2,5-dimethoxyaniline	-	mg/kg	0.005	ND
2,4,5-Trichloroaniline	-	mg/kg	0.01	ND
5-Amino-6-methylbenzimidazolone	-	mg/kg	0.005	ND
2,6- Diaminotoluene	-	mg/kg	0.002	ND
2,6-Dimethylaniline (2,6-DMA)	-	mg/kg	0.002	ND
4-Aminotoluene-3-sulfonic acid	-	mg/kg	0.005	ND
1,2-Phenylendiamine	-	mg/kg	0.002	ND
2,4-Dimethylaniline (2,4-DMA)	-	mg/kg	0.002	ND
5-Chloro-2-methylaniline	-	mg/kg	0.005	ND
2,5-Dichloroaniline	-	mg/kg	0.01	ND
2,4-Dinitroaniline	-	mg/kg	0.005	ND
2-Methoxy-4-nitroaniline	-	mg/kg	0.005	ND
p-Anisidine	-	mg/kg	0.002	ND
Dimethyl aminoterephthalate	-	mg/kg	0.002	ND
3,4-dichloroaniline	-	mg/kg	0.002	ND

Docusign Envelope ID: 4F33A0DB-2A37-85C5-8251-8A39808FB123

Fiesta Compostable/Recyclable, Fourth Way, Avonmouth, Bristol, BS11 8TB
Tel: 0117 316 5000 | Email: enquiries@fiestafoodtogo.com

1-Naphthylamine	-	mg/kg	0.002	ND
2-Aminobiphenyl	-	mg/kg	0.002	ND
Butyl Anthranilate	-	mg/kg	0.002	ND
2,4-Diaminodiphenylmethane	-	mg/kg	0.002	ND
2-Amino-5-methylbenzoic acid	-	mg/kg	0.002	ND
Conclusion				PASS

Notes :

(1) Test condition & simulant were specified by client.
(2) These tests were subcontracted to SGS Shanghai chemical lab.

(EU) No 10/2011 and its amendment (EU) 2020/1245 Regulation -Specific migration of heavy metal (For Sample ID 001)
Paper and board used in food contact materials and articles, EDQM-Specific migration of Lead(For Sample ID 002)

Test Method : With reference to EN13130-1:2004, analysis was performed by ICP-OES and ICP-MS.

Sample 001

Simulant Used : 3% Acetic acid (W/V)
Test Condition : 40 ℃ 2.0 hr(s)

Test Item(s)	Max. Permissible Limit	Unit	MDL	Test result
Migration times	-	-	-	First
Area/volume	-	dm^2/kg	-	6.0
Lead(Pb)	ND	mg/kg	0.01	ND
Aluminium(Al)	1	mg/kg	0.1	ND
Barium (Ba)	1	mg/kg	0.25	ND
Cobalt (Co)	0.05	mg/kg	0.01	ND
Copper (Cu)	5	mg/kg	0.25	ND
Iron(Fe)	48	mg/kg	5	ND
Lithium (Li)	0.6	mg/kg	0.1	ND
Manganese(Mn)	0.6	mg/kg	0.1	ND
Zinc(Zn)	5	mg/kg	0.5	ND
Nickel(Ni)	0.02	mg/kg	0.01	ND
Arsenic(As)	ND	mg/kg	0.01	ND
Cadmium(Cd)	ND	mg/kg	0.002	ND
Chromium(Cr)	ND	mg/kg	0.01	ND
Mercury(Hg)	ND	mg/kg	0.01	ND
Antimony(Sb)	0.04	mg/kg	0.01	ND

Docusign Envelope ID: 4F33A0DB-2A37-85C5-8251-8A39808FB123

Fiesta Compostable/Recyclable, Fourth Way, Avonmouth, Bristol, BS11 8TB
Tel: 0117 316 5000 | Email: enquiries@fiestafoodtogo.com

Europium (Eu)	-	mg/kg	0.025	ND
Gadolinium(Gd)	-	mg/kg	0.025	ND
Lanthanum(La)	-	mg/kg	0.025	ND
Terbium(Tb)	-	mg/kg	0.025	ND
Europium (Eu)+ Gadolinium(Gd)+ Lanthanum(La)+ Terbium(Tb)	0.05	mg/kg	-	ND
Conclusion				PASS

Sample 002

Simulant Used : 3% Acetic acid (W/V)
Test Condition : 40 ℃ 2.0 hr(s)

Test Item(s)	Max. Permissible Limit	Unit	MDL	Test result
Migration times	-	-	-	First
Area/volume	-	dm^2/kg	-	6.0
Lead(Pb)	ND	mg/kg	0.01	ND
Conclusion				PASS

Notes :

(1) Test condition & simulant were specified by client.
(2) For Sample ID 002:These tests was subcontracted to SGS Shanghai chemical lab.
Unless otherwise stated, the decision rule for conformity reporting is based on Binary Statement for Simple Acceptance Rule (w=0) stated in ILAC-G8:09/2019.